



Previous Name: Shell Morlina SD

Shell Morlina S3 BA 320

- Extra Protection
- Industrial Application
- Super Demulsification

Special Application Bearing & Circulating Oils

Shell Morlina S3 BA oils are premium quality rust & oxidation inhibited lubricating oils providing excellent lubrication in Morgoil® bearing & steel mill circulating systems. They are designed to have appropriate viscosity/temperature Characteristics, low foaming tendencies and excellent water separation properties. In addition, They protect equipment against corrosion and oil oxidation resulting in long service life. Meets the requirements of the Morgan and Danieli for super demulsibility applications.

DESIGNED TO MEET CHALLENGES

Performance, Features & Benefits

- **Long oil life – Maintenance saving**

Shell Morlina S3 BA oils are designed to give superior Oxidation resistance under high operating temperatures to give extended oil drain capability compared to basic bearing and circulating oils.

The excellent thermal and oxidative stability helps reduce the formation of sludge and other harmful oxidation products. The result is Extended oil life, less maintenance and less downtime.

- **Excellent rust & Corrosion protection**

Shell Morlina S3 BA oils are formulated with an effective additive package to help prolong the life of bearings and circulating systems through:

Enhanced water separation Characteristics that help ensure that critical oil films are retained between highly loaded parts in heavily contaminated environments

Good air release Characteristics to minimize cavitation and associated damage to circulating pumps

Helps protect against corrosion, even in the presence of water

- **Enhancing system efficiency**

Shell Morlina S3 BA oils have outstanding demulsibility and allow water to be shed rapidly from the oil. The water then may be removed by drainage or centrifuge from the lubrication system, thus protecting the installation against corrosion, premature wear & failure.

The excellent demulsibility also helps minimize the formation of emulsions which reduce filtration effectiveness, restrict circulation & promote bacterial growth. The use of

Main Applications



- **Morgoil® type bearing systems**

Approved for use in Morgoil® type bearing commonly found in steel mill applications. (Morgoil is a registered trademark of the Morgan Construction Company)

- **Heavily contaminated lubrication systems**

Shell Morlina S3 BA oils are recommended for circulating oil systems where water separation is a key issue.

- **Plain and rolling element bearings**

- **Industrial gear boxes**

Enclosed spur, helical, bevel and worm gearboxes where the use of a non-EP rust & oxidation inhibited oil is approved by the equipment manufacturer.

Specifications, Approvals & Recommendations

- Morgan Morgoil® Lubricant Specification New Oil (Rev. 1.1)
- Morgan MORGIL® Advanced Lubricant New Oil (Rev. 2.5)
- DIN 51517-1 - Type C
- DIN 51517-2 - Type CL
- AGMA 9005 for inhibited (R&O) Oils
- Danieli Standard Oil 6.124249F
- Danieli Super Demulsibility Oil 6.124249F

For a full listing of equipment approvals and recommendations, please consult your local Shell Technical Helpdesk.

fine filter filtration helps ensure effective contaminant free lubrication to critical machine parts.

Compatibility & Miscibility

- **Paint Compatibility**

Shell Morlina S3 BA Oils are compatible with seal materials and paints normally specified for use with mineral Oils.

Typical physical characteristics

Properties	Method	Morlina S3 BA 320
Viscosity Grade	ISO 3448	320
Gravity °API	ASTM D1298	26.1
Kinematic Viscosity @40°C	cSt ASTM D445	320
Kinematic Viscosity @100°C	cSt ASTM D445	23.1
Kinematic Viscosity @100°F	SUS Calculated	1483
Kinematic Viscosity @210°F	SUS Calculated	112
Viscosity Index	ASTM D2270	95
color	ASTM D1500	4
Pour Point	°C ASTM D5950	-6
Flash Point (COC)	°C ASTM D92	255
Acid Number	mg KOH/g ASTM D974	0.05
Cu Corrosion, 3 hrs @100°C	ASTM D130	1b
Rust, Synthetic Sea Water	ASTM D665B	Pass
Water Demulsibility @82°C	mins ASTM D1401	20
Water Demulsibility (ml of free Water before centrifuging) @52°C	ASTM D2711	32
Foam Test, Seq II	ml foam at 0/10 mins ASTM D892	30/0
Oxidation Control Test : TOST	hrs ASTM D943	1200+
Oxidation Control Test : RPVOT	mins ASTM D2272	400+
ANSI/AGMA Lubricant NO. 9005-D94		6

These Characteristics are typical of current production. While future production will conform to Shell's specification, variations in These Characteristics may occur.

Health, Safety & Environment

- Guidance on Health and Safety is available on the appropriate Material Safety Data Sheet, which can be obtained from <http://www.epc.shell.com/>

- **Protect the Environment**

Take used oil to an authorized collection point. Do not discharge into drains, soil or water.

Additional Information

- **Advice**

Product recommendations on applications not listed here may be obtained from your Shell representative.

Viscosity - Temperature Diagram for Shell Morlina S3 BA

